

INVESTIGATION OF THE MECHANICAL PROPERTIES OF CARBON NANOTUBES, UNDER THE INFLUENCE OF IMPERFECTIONS

MOHAMMAD MAHDI DEHGHAN PIR

A project report submitted in partial fulfilment of the
requirements for the award of the degree of
Master of Engineering (Mechanical)

Faculty of Mechanical Engineering
Universiti Teknologi Malaysia

JANUARY 2014

“Nothing exists except atoms and empty space”

This thesis is dedicated to all people who endeavor to develop knowledge, and to my beloved and kind parents who always supported me and filled my heart with nothing but their love and finally to all peaceful people of Iran.

This dissertation is dedicated to my family especially my lovely parents, Ibrahim and Parvin and my dear brother, Mostafa for the support they provided me through my entire life.

ACKNOWLEDGMENT

In the Name of God

I would like to express my deepest gratitude to PROF. DR.-ING. ANDREAS ÖCHSNER, who always advised and encouraged me with his perfect knowledge throughout the project. His constant support and invaluable suggestions made this work successful. This research project would not have been possible without the help of many people.

ABSTRACT

A carbon nanotube is a hollow cylinder, which is made of carbon atoms in the hexagonal lattice, which is made by rolling up the graphene sheet in the specific chiral vector direction. This cylindrical structure has outstanding mechanical, electrical thermal properties. Several attempts have been done to obtain the mechanical properties of CNTs in terms of Young's modulus, shear modulus, tensile strength etc. The finite element method has been used to obtain the Young's modulus of variety SWCNTs in this study. Furthermore, the imperfection (carbon vacancy) in the structure of SWCNT has been investigated on these models. Imperfection is one of the issues occurred in the producing of carbon structures such as graphene and carbon nanotubes and has a huge influence on mechanical properties of CNTs. This study consists of 68 different carbon nanotube models in three different types that are zigzag models from (3, 0) to (17, 0), armchairs from (2, 2) to (10, 10) and chiral models between (2, 2) and (10, 10). The imperfection percentages that investigated in this study are 5%, 10% and 15%. The results show that all models lose 34%, 56% and 90% of their tensile strength when they lost 5%, 10% and 15% of their carbon atoms from their structures (imperfection).

ABSTRAK

Satu tiub nano karbon adalah silinder berongga yang diperbuat daripada atom karbon dalam kekisi heksagon, yang dibuat oleh menggulung lembaran graphene dalam arah vektor kiral tertentu. Struktur silinder mempunyai mekanikal, sifat elektrik yang cemerlang terma. Beberapa percubaan telah dilakukan untuk mendapatkan sifat-sifat mekanik CNTs dari segi modulus Young, modulus ricih, kekuatan tegangan dan lain-lain. Kaedah unsur terhingga telah digunakan untuk mendapatkan modulus Young pelbagai SWCNTs dalam kajian ini. Tambahan pula, ketidaksempurnaan itu (karbon kekosongan) dalam struktur SWCNT telah disiasat pada model ini. Ketidaksempurnaan adalah salah satu daripada isu-isu yang berlaku dalam operasi penghasilan struktur karbon seperti graphene dan nanotube karbon dan mempunyai pengaruh yang besar ke atas sifat mekanik CNTs. Kajian ini terdiri daripada 68 berbeza model tiub nano karbon dalam tiga jenis yang berbeza yang model mabuk dari $(3, 0)$ kepada $(17, 0)$, kerusi-kerusi dari $(2, 2)$ hingga $(10, 10)$ dan model kiral antara $(2, 2)$ dan $(10, 10)$. Peratusan ketidaksempurnaan yang disiasat dalam kajian ini adalah 5%, 10% dan 15%. Keputusan menunjukkan bahawa semua model kehilangan 34%, 56% dan 90% daripada kekuatan tegangan mereka apabila mereka hilang 5%, 10% dan 15% daripada atom karbon mereka dari struktur mereka (ketidaksempurnaan).

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	II
	DEDICATION	III
	ACKNOWLEDGMENT	IV
	ABSTRACT	V
	ABSTRAK	VI
	TABLE OF CONTENTS	VII
	LIST OF TABLES	X
	LIST OF FIGURES	XI
	LIST OF ABBREVIATION	XII
	LIST OF APPENDICES	XIV
1	INTRODUCTION	
	1.1 Overview	1
	1.2 Problem Background	3
	1.3 Problem Statement	3
	1.4 Aim of the Project	3
	1.5 Objective of the Project	4
	1.6 Scope of the Project	4
	1.7 Organization of the Project	4
2	LITERATURE REVIEW	
	2.1 Introduction	6
	2.2 Carbon nanotube and its characteristics	7
	2.3 Finite element method (FEM)	11

2.3.1	Finite element models of C-C bonds	12
2.3.2	Properties of C-C bonds based on FEM	14
2.3.3	Perfect structure of CNT	17
2.3.4	Imperfect structure of CNT	18
2.4	Summary	20
3	RESEARCH METHODOLOGY	
3.1	Introduction	21
3.2	Research framework	21
3.2.1	Phase I: Perfect structures	23
3.2.1.1	The derivation of CNT characteristics	23
3.2.1.2	Finite element software (Marc)	24
3.2.2	Phase II: Imperfect structures	29
3.2.3	Phase III: Comparison	30
3.3	Summary	31
4	PERFECT STRUCTURE OF CNT	
4.1	Introduction	32
4.2	Perfect structure of CNTs	33
4.3	Armchair (10, 10) and zigzag (17, 0)	34
4.4	The results for zigzag models	36
4.5	The results for armchair models	38
4.6	Comparison between zigzag and armchair models	39
4.7	The results for chiral models	40
4.8	Validation	42
4.9	Summary	43
5	IMPERFECT STRUCTURE OF CNT	
5.1	Introduction	44
5.2	An overview of the investigation	44
5.3	Imperfection results for zigzag models	46
5.4	Imperfection results for armchair models	47
5.5	Imperfection results for chiral models	48
5.6	Conclusion	49

5.7 Future work	50
-----------------	----

REFERENCES	52
-------------------	-----------

APPENDICES	56
-------------------	-----------

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	MATERIAL AND GEOMETRIC PROPERTIES OF C-C BOND [12, 13, 14]	16
4.1	YOUNG'S MODULUS OF A (17, 0) ZIGZAG AND A (10, 10) ARMCHAIR CNT IN THREE OTHER REFERENCES.	36
4.2	THE YOUNG'S MODULI OBTAINED FOR DIFFERENT ZIGZAG SWCNTs	37
4.3	THE YOUNG'S MODULI OBTAINED FOR DIFFERENT ARMCHAIR SWCNTs	38
4.4	YOUNG'S MODULI (TPA) OBTAINED FOR CHIRAL MODELS (N , M)	41
4.5	THE VALIDATION OF THIS STUDY BASED ON TWO DIFFERENT INVESTIGATIONS	43
5.1	THE YOUNG'S MODULUS REDUCTION OF SWCNTs UNDER THE INFLUENCE OF DIFFERENT IMPERFECTION PERCENTAGE.	49

LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
2.1	SWCNT and MWCNT scheme	25
2.2	Parameters involved in chiral vector [12, 14]	26
2.3	Different direction of chiral vector	27
2.4	Top cross section of CNT	28
2.5	Carbon-carbon covalent bonds	30
2.6	FE modeling of C-C bonds in stretching	31
2.7	FE modeling of C-C bonds in bending	31
2.8	Perfect lattice of CNT	35
2.9	Imperfection in CNT	37
3.1	Research framework for designing and development of the proposed study	40
3.2	Nanotube modeler	42
3.3	MSC-Marc menu	43
3.4	Illustration of a beam element in a space frame [7]	44
3.5	Equivalence of molecular mechanics and structural mechanics for covalent and non-covalent interactions between carbon atoms. Molecular mechanics model (left) and structural mechanics model (right), adapted form [3]	45
3.6	The boundary condition for CNT in FEM package. The left picture is fixed nodes in bottom of the CNT and the write picture is applied fixed displacement nodes in z-direction in top of the CNT	46
4.1	Two different models of CNT. The left picture shows a zigzag (14, 0) and the right model shows an armchair (9, 9)	51
4.2	Two different chiral models. The left model shows a chiral (10, 1) and the right one	

	shows a chiral (10, 5)	52
4.3	Geometrical dimensions and applied boundary conditions on a (a) (10, 10) armchair and a (b) (17, 0) zigzag SWCNTs [12]	53
4.4	The Young's modulus comparison for perfect structure of zigzag models	55
4.5	The Young's modulus comparison for perfect structure of armchair models	57
4.6	Young's moduli comparison between armchair and zigzag models	58
4.7	Young's moduli obtained for chiral model of SWCNTs	60
5.1	Different kinds of carbon vacancy in SWCNT	63
5.2	Young's moduli of zigzag models under influence of different Imperfection percentage	64
5.3	Young's moduli of armchair models under influence of different Imperfection percentage	65
5.4	Young's moduli for different zigzag, armchair and chiral models under influence of different Imperfection percentage	66
5.5	Front view of the (a) perfect and (b) 10% perturbed structure of an Armchair SWCNT [12]	64

LIST OF ABBREVIATION

C	-	Carbon
CNT	-	Carbon Nanotube
SWCNT	-	Single-Wall Carbon Nanotube
MWCNT	-	Multi-Wall Carbon Nanotube
FEM	-	Finite Element Method
MD	-	Molecular Dynamic
CM	-	Continuum Mechanic
AFM	-	Atomic Force Microscope
TEM	-	Transmission Electron Microscope
A	-	Cross-section Area
L	-	Length of CNT
t	-	Thickness of CNT
b	-	C-C bond length
D	-	Diameter of CNT

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Young's moduli obtained for armchair models	56
B	Young's moduli obtained for zigzag models	57
C	Young's moduli obtained for chiral models	58

CHAPTER 1

INTRODUCTION

1.1 Overview

From the ancient, humans were looking for strong materials in order to apply them in their daily uses, wars and simply to be alive. Since that time people found iron and its carbon alloys are the strongest materials in the world. After improving the sciences and finding the importance of the atoms and interaction between them, scientists found the atomic structures made by pure carbon may have the strongest structures. The famous pure carbon structure is diamond which being considered as a strongest structure for long time.

After first observation of carbon nanotubes (CNT) by Iijima in 1991 [11], all efforts have been concentrated on deriving the finite element model (FEM) in order to investigate the properties of CNTs, such as Young's modulus, shear modulus and etc. Nowadays, it has been observed that carbon nanotubes are the strongest and stiffest materials yet discovered in terms of tensile strength and elastic modulus respectively. This strength results from the covalent bonds formed between the individual carbon atoms. Carbon nanotubes have outstanding Young's modulus, which is more than five times larger than stainless steel.

Beside the experimental investigations, many efforts have been done in order to investigate the mechanical properties of CNTs. Experimental and computational simulation such as molecular dynamics (MD) and continuum mechanics are the most important and useful methods in order to evaluate the characteristics of CNTs. The most powerful methods considered recently are computational methods due to the high costs involved in experimental to investigate the properties of CNTs. And the most commonly continuum mechanics technique is the finite element method (FEM), which is the computational approach to study the behaviors of CNTs. Based on these methods, different ranges of Young's modulus have been reported due to different length, different thickness or different computational or experimental approaches used to study the mechanical properties of CNTs. But, in most of them, the Young's modulus reported equal to 1 TPa approximately.

Li et al. [7] calculated the Young's modulus with respect to different nanotube diameters. They also, reported the Young's modulus ranges of CNTs are between 0.89 to 1.033 TPa. Changa et al. [5] represent the first effort to establish analytical methods of molecular mechanics and a set of examples that can be solved in closed form. They obtained that the Young's modulus is between 0.59 and 1.06 TPa. They reported for a given tube diameter, Young's modulus for armchair tubes is slightly larger than that for zigzag tubes.

Natsuki et al. [19] evaluated the Young's modulus ranges from about 0.5 TPa to more than 1.1 TPa depending on the wall thickness and the structure, whilst, Yu et al. [43] presented results of 15 SWCNT bundles under tensile load and found Young's modulus values in the range from 0.32 to 1.47 TPa. Krishnan et al. [42] of SWCNTs found an average modulus of about 1.3 ± 0.4 TPa for 27 SWCNTs.

1.2 Problem Background

Producing nano-materials or nano-structures due to non-precise facilities cause to have some problems in the perfect structure of CNTs. These problems are varying from doping other atoms, imperfection and perturbation of single carbon atoms and having all problems simultaneously in the structure of CNTs. However, because of lacking on experimental facilities in order to investigate the mechanical properties of CNTs specially disordered structures, the investigation based on computational methods such as continuum mechanics and FEM models have been considered recently.

1.3 Problem Statement

Since the first observation of single wall carbon nanotubes (SWCNTs) there have not been done any investigation on imperfect CNTs in all range of models. Finding a good description for imperfection models will be useful in order to know the effect of using these kinds of CNTs in composite materials. This study will answer to the question, what will happen to the Young's modulus of CNT if the structure will be affected by missing one or more carbon atoms and their related elements.

1.4 Aim of the Project

The goal of this project is to investigate the Young's modulus of imperfect CNTs and derive the best description of mechanical properties based on the imperfection percentage.

1.5 Objective of the Project

The objective of this project is to determine the Young's modulus as a property of different degrees of SWCNT under influence of imperfections.

1.6 Scope of the Project

The study is limited to the following scopes:

- i. Literature review on carbon nanotubes and imperfections.
- ii. Derive the finite element models for different SWCNT from Nanotube modeler.
- iii. MATLAB will be used to code the imperfection in the CNT structures.
- iv. The Finite element model of perfect and imperfect structure of CNTs will be evaluated in the MSC.Marc Mentat in order to investigate the Young's modulus.
- v. The comparison between perfect and imperfect structures will get the better description on the effects of imperfection on the CNTs.

1.7 Organization of the Project

This report covers six chapters, which are introduction, literature review and research methodology, derivation of Young's modulus of perfect structures based on literature reviews, obtaining the Young's modulus of imperfect structures based on the imperfection percentages, comparison of findings and discussion about the results. Chapter one includes the introduction of the study, the problem statement, aim of the study, the objective, scope of the study, general methodology. Chapter two provides background information and a review of related literatures that leads to

the problem statement. Chapter three provides the methodology of the study. In chapter four, the derivation of Young's modulus of perfect structures will be investigated and in chapter five, the Young's modulus of imperfect structures and the results will be discussed. The Young's modulus comparison between perfect and imperfect CNTs will be illustrated in chapter six and future work will be represented.

REFERENCES

1. Saito, R. (1998). Physical properties of carbon nanotubes (paperback).
2. Mohammadpour, E., Awang, M., & Abdullah, M. Z. (2011). Predicting the Young's Modulus of single-walled carbon nanotubes using finite element modeling. *J Appl Sci*, 11(9), 1653-1657.
3. Kalamkarov, A. L., Georgiades, A. V., Rokkam, S. K., Veedu, V. P., & Ghasemi-Nejhad, M. N. (2006). Analytical and numerical techniques to predict carbon nanotubes properties. *International Journal of Solids and Structures*, 43(22), 6832-6854.
4. Prabhu, S., Bhaumik, S., & B. K. Vinayagam. (2012) "Finite element modeling and analysis of zigzag and armchair type single wall carbon nanotube" *Journal of Mechanical Engineering Research* Vol. 4(8), pp. 260-266.
5. Changa, T., & Gao, H. (2003). Size-dependent elastic properties of a single-walled carbon nanotube via a molecular mechanics model. *Journal of the Mechanics and Physics of Solids*, 51(6), 1059-1074.
6. To, C. W. (2006). Bending and shear moduli of single-walled carbon nanotubes. *Finite Elements in Analysis and Design*, 42(5), 404-413.
7. Li, C., & Chou, T. W. (2003). A structural mechanics approach for the analysis of carbon nanotubes. *International Journal of Solids and Structures*, 40(10), 2487-2499.
8. Li, C., & Chou, T. W. (2003). Elastic moduli of multi-walled carbon nanotubes and the effect of van der Waals forces. *Composites Science and Technology*, 63(11), 1517-1524.
9. Ebbesen, T. W., & Takada, T. (1995). Topological and SP³ defect structures in nanotubes. *Carbon*, 33(7), 973-978.

10. Li, C., & Chou, T. W. (2004). Modeling of elastic buckling of carbon nanotubes by molecular structural mechanics approach. *Mechanics of Materials*, 36(11), 1047-1055.
11. Iijima, S. (1991). Helical microtubules of graphitic carbon. *nature*, 354(6348), 56-58.
12. Öchsner, A., & Rahmandoust, M. (2009). Influence of structural imperfections and doping on the mechanical properties of single-walled carbon nanotubes. *Journal of Nano Research*, 6, 185-196.
13. Öchsner, A., Ghavamian, A., & Rahmandoust, M. (2012). A numerical evaluation of the influence of defects on the elastic modulus of single and multi-walled carbon nanotubes. *Computational Materials Science* 62, 110–116.
14. Rahmandoust, M., & Ochsner, A. (2012). On finite element modeling of single- and multi-walled carbon nanotubes. *Journal of nanoscience and nanotechnology*, 12(10), 8129-8136.
15. Öchsner, A., Ghavamian, A., & Rahmandoust, M. (2013). On the determination of the shear modulus of carbon nanotubes. *Composites: Part B* 44, 52–59.
16. Hu, N., Nunoya, K., Pan, D., Okabe, T., & Fukunaga, H. (2007). Prediction of buckling characteristics of carbon nanotubes. *International Journal of Solids and Structures*, 44(20), 6535-6550.
17. Iijima, S. (1993). Growth of carbon nanotubes. *Materials Science and Engineering: B*, 19(1), 172-180.
18. Iijima, S. (2002). Carbon nanotubes: past, present, and future. *Physica B: Condensed Matter*, 323(1), 1-5.
19. Natsuki, T., Tantrakarn, K., & Endo, M. (2004). Prediction of elastic properties for single-walled carbon nanotubes. *Carbon*, 42(1), 39-45.
20. Canadija, M., Brcic, M., & Brnic, J. (2013). Bending behaviour of single-layered graphene nanosheets with vacancy defects. *Engineering Review*, 33(1), 9-14.
21. Lu, X., & Hu, Z. (2012). Mechanical property evaluation of single-walled carbon nanotubes by finite element modeling. *Composites Part B: Engineering*, 43(4), 1902-1913.
22. Kang, Z., Li, M., & Tang, Q. (2010). Buckling behavior of carbon nanotube-based intramolecular junctions under compression: Molecular dynamics

- simulation and finite element analysis. *Computational Materials Science*, 50(1), 253-259.
23. Xiao, J. R., Gama, B. A., & Gillespie Jr, J. W. (2005). An analytical molecular structural mechanics model for the mechanical properties of carbon nanotubes. *International Journal of Solids and Structures*, 42(11), 3075-3092.
 24. M, Meo. (2006). Prediction of Young's modulus of single wall carbon nanotubes by molecular-mechanics based finite element modeling, Vol. 66, Issues 11–12, Pages 1597–1605
 25. Meo, M., & Rossi, M. (2007). A molecular-mechanics based finite element model for strength prediction of single wall carbon nanotubes. *Materials Science and Engineering: A*, 454, 170-177.
 26. B.I.Yakobson and A.Rubio "Elastic and Inelastic Mechanical Properties." *Nanotubular Structures: Characterization and Simulation in the Atomic Scale* (2001)
 27. Yakobson, B. I., & Couchman, L. S. (2004). Carbon nanotubes: Supramolecular mechanics. *Encyclopedia of Nanoscience and Nanotechnology*, 587.
 28. Rangel, J. H., Brostow, W. I. T. O. L. D., & Castano, V. M. (2013). Mechanical modeling of a single-walled carbon nanotube using the finite element approach. *Polimery*, 58(4), 276-281.
 29. Qian, D., Wagner, G. J., Liu, W. K., Yu, M. F., & Ruoff, R. S. (2002). Mechanics of carbon nanotubes. *Applied Mechanics Reviews*, 55(6), 495-533.
 30. Kis, A., & Zettl, A. (2008). Nanomechanics of carbon nanotubes. *Philosophical Transactions of the Royal Society A: Mathematical, Physical and Engineering Sciences*, 366(1870), 1591-1611.
 31. Y, Ying. S, Guangyu. & Z, Peng. (2011). Frequency Study of Single-walled Carbon Nanotubes Based on a Space-frame Model with Flexible Connections. *JOURNAL OF COMPUTERS*, VOL. 6, NO. 6.
 32. Nahas, M. N., & Abd-Rabou, M. A. H. M. O. U. D. (2010). Finite element modeling of carbon nanotubes. Submitted to *Computational Materials Science*.
 33. Tserpes, K. I., & Papanikos, P. (2005). Finite element modeling of single-walled carbon nanotubes. *Composites Part B: Engineering*, 36(5), 468-477.

34. S, Noorizadeh. & E, Shakerzadeh. (2012). Formaldehyde adsorption on pristine, Al-doped and mono-vacancy defected boron nitride nanosheets: A first principles study. *Computational Materials Science*, 56 122–130.
35. Philip G. Collins. (2009) “Defects and disorder in carbon nanotubes”. University of California at Irvine, Irvine, USA. PHD Thesis.
36. Muc, A. (2011). Modelling of carbon nanotubes behaviour with the use of a thin shell theory. *Journal of Theoretical and Applied Mechanics*, 49(2), 531-540.
37. Qian, D., Wagner, G. J., Liu, W. K., Yu, M. F., & Ruoff, R. S. (2002). Mechanics of carbon nanotubes. *Applied Mechanics Reviews*, 55(6), 495-533.
38. Duan, W. H., Wang, Q., Liew, K. M., & He, X. Q. (2007). Molecular mechanics modeling of carbon nanotube fracture. *Carbon*, 45(9), 1769-1776.
39. Ruoff, R. S., Qian, D., & Liu, W. K. (2003). Mechanical properties of carbon nanotubes: theoretical predictions and experimental measurements. *Comptes Rendus Physique*, 4(9), 993-1008.
40. Salvetat, J. P., Briggs, G. A. D., Bonard, J. M., Bacsá, R. R., Kulik, A. J., Stöckli, T., ... & Forró, L. (1999). Elastic and shear moduli of single-walled carbon nanotube ropes. *Physical Review Letters*, 82(5), 944.
41. Salvetat, J. P., Bonard, J. M., Thomson, N. H., Kulik, A. J., Forro, L., Benoit, W., & Zuppiroli, L. (1999). Mechanical properties of carbon nanotubes. *Applied Physics A*, 69(3), 255-260.
42. Krishnan, A., Dujardin, E., Ebbesen, T.W., Yianilos, P.N., Treacy, M.M.J., 1998. Young's modulus of single-walled nanotubes. *Physical Review B* 58 (20), 14013–14019.
43. Yu, M.F., Files, B.S., Arepalli, S., Ruoff, R.S., (2000). Tensile loading of ropes of single wall carbon nanotubes and their mechanical properties. *Physics Review Letters* 84 (24), 5552–5555.
44. Tombler, T.W., Zhou, C., Alexseyev, L., Kong, J., Dai, H., Liu, L., Jayanthi, C.S., Tang, M., Wu, S.-Y., (2000). Reversible electromechanical characteristics of carbon nanotubes under local-probe manipulation. *Nature* 405, 769–772.